

# SURFACE™

## SL-QS.neo

by tecnodry

Self-leveling rapid-drying mortar with ultra-high compressive strength

☎ (+52) 55 4845 7585

🇨🇦🇺🇸 (+1) 661 379-6105

✉ info@self-leveling.us

- Fast-Setting hydraulic leveling mortar with accelerated dry time
- Ultra-high strength
- Excellent for poorly finished, uneven, or flawed surfaces requiring optimal leveling at thick applications
- Zero-shrink formulation
- Application thickness 1/16" to 2.75"



### Key Advantages

- Easy to apply with excellent flowability
- Supports light foot traffic 2–3 hours after application (varies by thickness)
- Fast-setting with ultra-high strength

### Technical information

Physical appearance, 55 lb (25 kg) bag	Light gray powder
Water amount per bag (thickness 1/16"–3/8")	1.36 gallons
Water amount per bag (thickness 3/8"–2.75")	1.19 gallons
Working time	20 minutes
Curing time for floor installation	6 to 48 hours
Compressive strength @ 28 days (ASTM C109)	10,100 PSI
Flexural strength @ 28 days (ASTM C348)	1,065 PSI

<sup>1</sup> mix with 1.19 US gallons of water per 55 lb bag (for thicknesses 3/8" to 2-3/4")



Technical Data Sheet

